

Applicant: XIAMEN GREEN MOUNTAIN
22/F., BUILDING 2,
THAIHOT PLAZA XIUFENG ROAD,
FUZHOU 350012 FUJIAN CHINA
Attn: LILY

Date: Jun 11, 2020


Sample Description:

One (1) pair of submitted samples said to be ICE TECH GETA GRIP GM-144 outsoles
Test Method : SATRA TM144: 2011
Colour : Black
Date Received/Date Test Started: Jun. 05, 2020
Date Final Information Confirmed: --

Test Result Please Refer To Attached Page(S).

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Guiliang Dong
Senior Lab Manager



Slip Resistance (SATRA TM144: 2011, Ice Surface At -7°C, Vertical Force: 500 N)

| | | <u>Applicant's Requirement</u> |
|----------|---|--------------------------------|
| | The 1 st Run (Initial Frosted Surface) | |
| Heelpart | 0.37 | - |
| Forepart | 0.35 | - |
| | The 2nd Run (Black Ice (Wet Ice)) | |
| Heelpart | 0.32 | - |
| Forepart | 0.28 | - |
| | The 3rd Run (Black Ice (Wet Ice)) | |
| Heelpart | 0.31 | - |
| Forepart | 0.26 | - |
| | The 4th Run (Relatively Smoother Ice (Black Ice)(Wet Ice)) | |
| Heelpart | 0.27 | - |
| Forepart | 0.22 | - |

Note:

1. The Outsole Of Test Sample Was Pre-Chilled To -7°C In Water-Ethanol Bath Before Testing.
2. It Must Be Noted That The Slip Resistance Test Carried Out In This Report Denotes An Indication Of Slip Of This Particular Footwear/Component On The Surface Mentioned In The Test Item. It Is Important To Note That Footwear Is Subject To Many Different Conditions Encountered In Everyday Use And That It Is Impossible To Make Footwear Resistant To Slip In All Conditions. Nevertheless, It Is Generally Accepted That Problems Are Minimized If The Guideline Coefficients Of Friction Are Achieved.

Expanded Uncertainty: 0.01, With k = 2 At 95% Confidence Level.



End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.